

<b>Veröffentlichungsnummer:</b>	JP64000105 (A)	<b>Auch veröffentlicht als</b>  JP2535922 (B2)
<b>Veröffentlichungsdatum:</b>	1989-01-05	
<b>Erfinder:</b>	CHIGUSA TOSHIICHI; MORI MITSUHIRO; KONDO YOZO	
<b>Anmelder:</b>	TOSOH CORP.	
<b>Klassifikation:</b>		
- Internationale:	C08F4/64; C08F4/60; C08F10/00; C08F4/00; C08F10/00; (IPC1-7): C08F4/64; C08F10/00	
- Europäische:		
<b>Anmeldenummer:</b>	JP19870154556 19870623	
<b>Prioritätsnummer(n):</b>	JP19870154556 19870623	
<b>INPADOC Patentfamilie anzeigen</b>		
<b>Liste der Anführungen anzeigen</b>		
Datenfehler hier melden		

#### Zusammenfassung von JP 64000105 (A)

**PURPOSE:** To produce the title polyolefin having a low fine particle content, a suitable mean particle diameter and a high bulk density in high yields, by using a catalyst comprising a specified solid catalyst component, a specified promotor and an electron-donating compound. **CONSTITUTION:** A 3C or higher alpha-olefin is polymerized by using a catalyst system comprising a solid catalyst component (A) obtained by reacting a homogeneous solution containing at least one compound selected from a mixture of metallic magnesium with a hydroxylated organic compound and an organic oxygen compound of Mg, an electron-donating compound and an organic oxygen compound of Ti with at least one aluminum halide compound and reacting the obtained solid product with a surfactant, an electron-donating compound and a titanium halide compound and at least one organoaluminum compound (B); and an electron-donating compound (C). A highly stereoregular polyolefin of a low fine particle content, a suitable mean particle diameter and a high bulk density can be obtained.

Daten sind von der **esp@cenet** Datenbank verfügbar — Worldwide